

TECHNICAL DATA

PRODUCT NAME		4 MIL SAFETY FILM
1	% Visible light transmittance	90
2	% Visible light Reflectance	9
3	% Solar Energy Transmittance	83
4	% Solar Energy Reflectance	6
5	% Solar Energy Absorptance	11
6	% UV transmittance	<2
7	% Total Solar Energy Rejected	13
8	U-Factor Day Winter	1.12
9	Shading Coefficient	0.98
10	Emmissivity	0.89
11	% Glare Reduction	1
12	% Solar Heat Reduction	2
Note : All values as applied to 1/8 inch clear glass. Test results are representative of actual production and may vary from batch to batch.		