

TECHNICAL DATA

PRODUCT NAME		C-4 MIL HP NAT-50
1	% Visible light transmittance	52
2	% Visible light Reflectance	9
3	% Solar Energy Transmittance	51
4	% Solar Energy Reflectance	9
5	% Solar Energy Absorptance	40
6	% UV transmittance	<1
7	% Total Solar Energy Rejected	38
8	U-Factor Day Winter	1.14
9	Shading Coefficient	0.73
10	Emmissivity	0.85
11	% Glare Reduction	42
12	% Solar Heat Reduction	27
Note : All values as applied to 1/8 inch clear glass. Test results are representative of actual production and may vary from batch to batch.		